

Melton Classics, Inc.
PlasterCast™
PRE FABRICATED GLASS FIBER
REINFORCED GYPSUM COLUMNS AND FORMS
Section 09275

PART 1 GENERAL:

1.01 WORK COVERED:
Manufacturer of GRG (Glass Fiber Reinforced Gypsum) Forms

1.02 RELATED WORK IN OTHER SECTIONS:
A. Light gauge metal framing.
B. Veneer gypsum plaster.
C. Gypsum board.
D. Finishing glass fiber reinforced gypsum.
E. Miscellaneous metals.

1.03 SUBMITTALS:
Samples and shop drawings to conform to Section 01200
A. Samples:
Samples submitted as required by architect.
B. Shop Drawings:
Submit shop drawings completely detailing prefabricated glass fiber suspension systems, outlet boxes, and other items which occur in or are affected by prefabricated gypsum members shall be prepared at the factory by manufacturer only for those items indicated on approved shop drawings.

1.04 STANDARDS OF PERFORMANCE, DESIGN AND QUALITY:
A. Manufacturers Qualifications:
Melton Classics, Inc. has a demonstrated capability to produce GRG
B. All GRG forms shall match approved samples.

C. All GRG forms will be installable according to details submitted in shop

PART 2 PRODUCTS:

2.01 MANUFACTURER:
Melton Classics, Inc.
P.O. Box 465020
Lawrenceville, GA 30042
(770) 963-3060 (800) 963-3060 Fax: (770) 962-6988

2.02 MATERIALS:

- A. Description: Glass Fiber Reinforced Gypsum (GRG)
1. Pre molded GRG parts are fabricated to details and dimensions
 2. Finished product shall conform to the following standards.

PHYSICAL PROPERTIES OF GRG "FIBROCAL"

- a. Shell Thickness:
3/16" minimum except for small components which may be
1/8" minimum, large components such as wall panels shall
- b. Weight: 1.5 lbs. per square foot
- c. Flexural Strength: 4,192 psi
- d. Tensile Strength: 1,340 psi
- e. Compressive Strength: 5,800 psi
- f. Density: 110 lbs. per cubic foot
- g. Hardness (Barcol): 105
- h. Flammability:
Flame Spread 0
Smoke Developed 0
ASTM E4 Class A
- i. Glass Content: 38.7%

3. All parts to contain supports as required to keep within allowable
4. Finish surfaces shall be true or textured according to design

2.03 FABRICATION:

- A. Molds to be constructed of reinforced fiberglass to produce units
- B. Allowable Tolerances:
1. Dimensional Tolerances: $\pm 1/8"$
 2. Wall Thickness: Nominal 3/16"
 3. Out of Plumb: $\pm 1/8"$
 4. Bowing: L/360 Maximum

PART 3 EXECUTION

3.01 INSTALLATION

- A. General:

- B. Employ only workmen experienced, skilled and trained on this type of Workmanship:
Install work of this section complete, straight, plumb, level, in true
- C. Erection:
GRG forms shall be installed per drawings, including the approved shop
- D. Sealing and Caulking:
Shall conform to requirements of Caulking and Sealing Section 07900 and requirements indicated and specified herein.
 - 1. Joints and Sealants: Joints (quantity, sizes, and shapes) indicated
- E. Finishing Materials:
 - 1. Fasteners:
As indicated on approved shop drawings and in accordance with
 - 2. Joint treatment materials:
 - a. General: ASTM C-475; type recommended by the
 - b. Joint tape: Perforated type.
 - c. Joint Compound: Ready Mixed vinyl-type for interior use.
(1) Grade: 2 separate grades; one specifically for bedding
 - 3. Miscellaneous Materials:
 - a. General: Provide auxiliary material for work of types and
 - b. Adhesive: Special adhesive recommended for laminating
- F. Replacements:
 - 1. In-place GRG forms may be rejected for the following
 - a. Nonconformance to detail requirements specified
 - b. Nonconformance with approved samples.
 - c. Nonconformance to specified fabrication or installation
 - d. Damage beyond satisfactory field repair, as determined by

3.02 CLEANUP:
General:
Perform cleaning procedures as recommended by GRG unit manufacturer.

3.03 GUARANTEE:
One year from substantial completion.